

Brass Spray

Introduction

Technical sprays are used in nearly all sectors of modern industry. These sprays are used for care and protection of surfaces, for cleaning, degreasing, dissolving and separating and are essential in daily business.



WEICON Brass Spray is a purely metallic coating in the typical brass colour. It is suited for the protection and optical refinement of various materials.

Applications

- Restoration work
- Decorative purposes like picture frames
- Applied art, hobbies, and crafts
- Subsequent refining of yellow-chromated parts that have been damaged due to drilling, welding, or milling.

Technical data

Colour	brass-metallic, matt	
Application	Indoors and outdoors	
Binding agent	Acrylic resin	
Pigment	Brass pigments	
Pigment purity	about 99,9% Ms	
Percentage of metal in dry film	about. 52 %	
Content	400 ml	
Specific weight	0,9 - 1,0 g/cm ³	
Recommended primer	Zinc Spray	
Processing temperature	+5 to +35, optimum temperature from +18 to + 25 °C	
Consumption at 1.5 cross coats	about. 120 ml/m ²	
Layer thickness at 1.5 cross coats	about. 20-30 µm	
dust dry after	about. 10 Min.	
Hardened after	about. 4-6 h	
paintable	about. 4-6 h	
Abrasion-resistant	abrasion-resistant	
Cross cutting DIN 53151 / ISO 2409	Cross cut characteristic value GT 0 to GT 1	
Salt spraying test DIN 50021 / DIN 53167	- - - h	
Mandrel bend test DIN EN ISO 1519	no hair cracking	
Top coating	not required	
Temperature resistance after complete hardening	about -50 to +300 °C	
Storage stability	24 months	

Pretreatment of the surface

Clean and degrease surfaces with WEICON Cleaner S.

Processing

Clean and degrease surfaces with Cleaner S. Shake can before use till the mixing ball can be heard. Spray on evenly and crosswise at room temperature (approx. +20°C) and at about 25 cm distance from surface. Dust-dry after approx. 10 minutes, fully hardened after approx. 4-6 hours.

Storage

Pressurized container: protect from sunlight and do not expose to temperatures exceeding +50°C.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation.

We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG (Headquarter)

Königsberger Str. 255 · DE-48157 Münster
P.O. Box 84 60 · DE-48045 Münster
Germany

Tel. +49 (0) 251 / 93 22-0
Fax +49 (0) 251 / 93 22-244
Fax +49 (0) 251 / 93 22-233 Export
www.weicon.de · info@weicon.de

WEICON Middle East L.L.C.

Jebel Ali Ind Area 3 · P.O. Box 118 216
Dubai · U.A.E

Phone +971 4 880 25 05
Fax +971 4 880 25 09
Mobile +971 50 545 99 83
www.weicon.ae · info@weicon.ae

WEICON Inc.

20 Steckle Place · Unit 20
Kitchener · Ontario · N2E 2C3
Canada

Phone +1 519 896 5252
Fax +1 519 896 5254
Cell +1 519 590 5168
www.weicon.ca · info@weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.

Yenibosna Mahallesi Yalçın Koreş Caddesi
Arifağa Sokak No: 29 Kat: 3
34530 Yenibosna – İstanbul Turkey
www.weicon.biz.tr · info@weicon.biz.tr

WEICON Romania SRL

Str. Depozitelor 22
540240 Targu Mures, jud. Mures Romania
www.weicon.com · office@weicon.com