

# Contact VA 8312

Create Date: 25.06.2013 - Page 1/1

## Introduction

WEICON Contact Cyanoacrylate Adhesives are cold curing one-component adhesives, free of solvents. They quickly polymerise by reacting with moisture both on the surfaces to be bonded and from the air, and cure under light pressure.



- low viscosity, 20-40 mPa·s
- very fast-curing
- for bonding of numerous rubber materials (e.g. solid rubber or cellular rubber) and plastics
- especially suitable for bonding of EPDM elastomers
- also suitable for bonding polyolefines (PE-Polyethylene, PP Polypropylene) in combination with WEICON CA-Primer
- the ideal adhesive in combination with WEICON Filler for instant bonding and filling of cracks, gaps, holes and irregularities

## Technical data

Ester type	Ethyl
Condition / nature	colourless, clear liquid
Viscosity at +20°C Brookfield	20-40 mPa·s
Max. gap covering	0,1 mm
Initial adhesion on Aluminium	30-60 sec.
Initial adhesion on Nora test rubber	2-10 sec.
Initial adhesion on Rigid PVC	5-30 sec.
Final strength after	24 h

## Pretreatment of the surface

- To ensure a perfect bonding, the surfaces to be joined must be clean and dry (to clean and degrease use e.g. WEICON Cleaner S).
- Smooth surfaces should be mechanically roughened.

## Processing

- Apply WEICON Contact Cyanoacrylate Adhesive only on one of the surfaces to be bonded.
- The bond line should be between 0.05 mm and max. 0.2 mm in thickness. Otherwise complete hardening cannot be guaranteed.
- For bonding large surfaces WEICON Contact Cyanoacrylate Adhesive should be applied drop by drop to avoid inner tensions.
- WEICON Contact Cyanoacrylate Adhesives are very economical. One drop is sufficient to cover approx. 3 - 5 cm<sup>2</sup> of bonded surface.
- The parts to be joined should be bonded in an atmosphere of 40 - 80 % relative humidity. In conditions of below 40%, the cure will be considerably slowed or even inhibited. With a relative air humidity of

more than 80% or with basic substrates (e.g. glass), shock-curing can occur. In such cases, some materials show a drop in bond strength of 10 - 15 %, due to inner tensions in the bond line.

- Basic-reacting surfaces (pH-value >7) will speed up the cure whereas acidic-reacting surfaces will retard and, under extreme conditions, completely inhibit the polymerization.

## Storage

WEICON Contact Cyanoacrylate Adhesives should always be stored in a cool, dry and dark place. The shelf life is at least 9 months if stored at room temperature (18 - 25°C). If stored at +5°C (e.g. in a refrigerator), the shelf life can be extended to 12 months.

## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

### WEICON GmbH & Co. KG (Headquarter)

Königsberger Str. 255 · DE-48157 Münster  
P.O. Box 84 60 · DE-48045 Münster  
Germany

Tel. +49 (0) 251 / 93 22-0  
Fax +49 (0) 251 / 93 22-244  
Fax +49 (0) 251 / 93 22-233 Export  
www.weicon.de · info@weicon.de

### WEICON Middle East L.L.C.

Jebel Ali Ind Area 3 · P.O. Box 118 216  
Dubai · U.A.E

Phone +971 4 880 25 05  
Fax +971 4 880 25 09  
Mobile +971 50 545 99 83  
www.weicon.ae · info@weicon.ae

### WEICON Inc.

20 Steckle Place · Unit 20  
Kitchener · Ontario · N2E 2C3  
Canada

Phone +1 519 896 5252  
Fax +1 519 896 5254  
Cell +1 519 590 5168  
www.weicon.ca · info@weicon.ca

### WEICON Kimya Sanayi Tic. Ltd. Şti.

Yenibosna Mahallesi Yalçın Koreş Caddesi  
Arifağa Sokak No: 29 Kat: 3  
34530 Yenibosna – İstanbul Turkey  
www.weicon.biz.tr · info@weicon.biz.tr

### WEICON Romania SRL

Str. Depozitelor 22  
540240 Targu Mures, jud. Mures Romania  
www.weicon.com · office@weicon.com